

# TECHNICAL DATASHEET

SVP 52

Dec. 2021

## SILICONE COATING

### PRODUCT DESCRIPTION

SVP52 is a flexible, transparent modified silicone resin conformal coating. It may be soldered through to allow rework. It is suitable for dip coating, spraying and brushing.

### PRODUCT USE

SVP52 is for use in the protection of electronic circuitry to meet the highest defence and aerospace industry requirements. Common uses include in telecommunications, radar and associated applications.

### FEATURES

- Excellent adhesion under all climatic conditions
- Excellent resistance to mould growth and ultra violet light, and to prolonged exposure to tropical life and salt spray
- Wide temperature range -60°C to 200°C
- High gloss finish and high surface resistivity
- Coating thickness typically being 25 to 50 microns
- Fluorescent under ultra violet light as an aid to subsequent inspection
- Can be soldered through without fear of highly toxic gases being produced
- Halogen free.

### APPLICATION

SVP52 can be sprayed, dipped or brushed. The thickness of the coating depends on the method of application, but a dip coater normally deposits a film thickness of about 25 microns (single coat). Workshop temperatures of less than 16°C or relative humidities in excess of 75% are unsuitable for the application of SVP52. All PCBs, being composite materials, absorb moisture. If this is not removed, the conformal coating may not protect to its fullest extent. Pre-drying, or better still, vacuum desiccation, will remove most of the moisture.

SVP52 contains a UV trace which allows inspection of the PCB after coating to ensure complete and even coverage. The stronger the reflected light, the thicker the coating layer is.

### CLEANING

Boards should be thoroughly cleaned before coating and moisture exempt. This is required to ensure that satisfactory adhesion to the substrate is possible. Also all flux residues must be removed as they become corrosive if left on the PCB. ABchimie manufacture a range of 100% Ozone

Friendly cleaning products in both the hydrocarbon solvent and aqueous fields. Please contact ABchimie for further information.

## **DIP COATING**

Ensure that the coating material in the container has been agitated thoroughly and has been allowed to stand for at least 2 hours for all the air bubbles to disperse.

SVP52 Thinners (DVS) should be used to keep the SVP52 coating at a suitable viscosity for dipping. DVS is added periodically as the solvent evaporates. The viscosity should be checked using a viscosity meter or "flow cup".

The board assemblies should be immersed in the SVP52 dipping tank in the vertical position, or at an angle as close to the vertical as possible. Connectors should not be immersed in the liquid unless they are very carefully masked. ABchimie Peelable Coating Mask (LDM) is ideal for this application.

Leave submerged for about 1 minute until the air bubbles have dispersed. The board or boards should then be withdrawn VERY SLOWLY (5 to 20 centimetres/mn) so that an even film covers the surface. After withdrawing, the boards should be left to drain over the tank until the majority of residual coating has left the surface.

After the draining operation is complete, the boards should be placed in an air-circulating drying cabinet and left to dry for 2 hours at room temperature prior to any heat curing.

## **SPRAYING**

SVP52 can be diluted with SVP52 Thinners (DVS) before spraying. The optimum viscosity to give coating quality and thickness depends on the spray equipment and conditions but a starting point could be 2 parts coating to 1 part thinners. If bulk coating material has been agitated, allow to stand until air bubbles have dispersed.

SVP52 is suitable both for use in manual spray guns and computer controlled airless spray equipment that only coats the required areas of the PCB, eliminating the need for masking. The nozzle of the spray gun requires to be selected to give an even spray to suit the prevailing viscosity of the coating material.

To ensure penetration of the coating beneath the components and in confined spaces, spray the assembly from all directions to give an even coating.

After spraying, the boards should be placed in an air-circulating drying cabinet and left to dry for 2 hours at room temperature prior to any heat curing.

## **BRUSHING**

Ensure that the coating material has been agitated thoroughly and has been allowed to settle for at least 2 hours. The coating should be kept at ambient temperature. Gently apply the coating with a good quality brush (silk) so as not to leave brush marks and so that the components and wiring are not disturbed.

When the brushing operation is complete the boards should be placed in an air-circulating drying cabinet and left to dry for 2 hours at room temperature prior to any heat curing.

## DRYING TIMES AND CURING CONDITIONS

SVP52 will be touch dry at room temperature after 2 hours and continue to cure during 24 hours at room temperature. If you need a solvent resistance for your application, you can heat it until 70°C during 2 hours or 4 hours at room temperature.

For application in line the following process can be applied:

- Dispensing
- Extraction zone 2-3 minutes
- Oven at 70-80°C 10 minutes

## PLASTIC COMPATIBILITY

Please note the solvent system for this product contains Xylene which could possibly affect polystyrene and polycarbonates.

## TYPICAL PROPERTIES

### **Liquid SVP52 :**

Colour:	Clear Pale Straw
Non-volatile Content:	45% approx (bulk material)
Viscosity @ 20°C (Zahn 2):	60 - 120 cSt (bulk material)
Specific Gravity @ 20°C:	0.97(bulk)
Flash Point:	25°C

### **Dried SVP52 Coating :**

Insulation resistance ( $\Omega$ )	$10^{12}$ (MIL-I-46058C)
Dielectric withstanding voltage VRT	> 1500V (MIL-I-46058C)
Thermal chocking	-25°C +25°C, 100 cycles, palier 15min, 5°C/min
SIR Test 15H	-25°C +50°C, 50 cycles, 15min/15min
Moisture resistance (d�ei water)	20°C-80°C, 90%RH, sous tension
Salt resistance (fog)	10-80°C, 95%RH +-4%, 90 jours
Dielectric Strength:	NF X41-002, 600 Hours, salt solution 5%
Electrical Resistivity	90kV/mm
Temperature Range:	$1 \times 10^{15}$ Ohms/cm
Thermal expansion coefficient	-60°C to +200°C
	90 ppm/°C

## AVAILABLE PACKAGING

### **SVP52 Conformal Coating**

1 Litre Bulk	SVP52 01L
5 Litre Bulk	SVP52 05L

### **SVP52 Conformal Coating – black version**

5 Litre Bulk SVP52 B 05L

### **SVP52 Thinners**

5 Litre Bulk DVS05L

### **Cleaners:**

5 Litre Bulk SND 05L

30 Litre Bulk SND 30L

### ***No toxic cleaner***

5 Litre Bulk DNS 05L

30 Litre Bulk DNS 30L

The conformal coating SVP52 is compliance with REACH and ROHS regulations. If you want a certificate, please contact us ([info@abchimie.com](mailto:info@abchimie.com)).

### **Storage:**

Storage temperature: 5 to 30°C

A temporary lower temperature during few days (transport) doesn't distort varnish properties.

**Date by use:** 18 months after the date of manufacturing

*All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. ABchimie cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.*